



## PPG LABORATORY TEST RESULTS CERTIFICATION

### ALKALI RESISTANCE SODIUM HYDROXIDE

PPG Industries, Inc. certifies the following performance properties for the Duranar® Coil Coating System when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

**COATING:** DURANAR PLUS

**TEST:** ASTM D1308 - Reagent 6.1.5, Procedure 7.2

**SPECIFICATION:** A coated panel is subjected to a 10% and 25% sodium hydroxide spot test for a period of 1 hour. The panel is then washed with distilled water, and examined for any effects of significant color change, blisters and overall appearance.

**RESULTS:** No significant effect on coating.

May 1, 2002